

Weathercoat™

High Performance Acrylic Weatherproofing Coatings

DSC432

Description

The right choice for changing the colour of an existing EIFS finish or other exterior surfaces. Weathercoat is an exterior 100% acrylic smooth coating which is offered in a variety of standard colours as well as custom colours. Weathercoat contains the most effective ingredients available to help resist mold and mildew growth.

Uses

Weathercoat is a durable coating which may be used to protect and decorate masonry, stucco, wood, primed metal and acrylic-based textured finishes such as EIFS finishes.

Coverage

Weathercoat is supplied in one 19 L (5 gallon) pail. Coverage will vary depending upon substrate, surface texture, environmental conditions and application technique. The coverage of the first coat on textured surfaces can vary from 33-74 m² (350-800 ft²) per pail depending upon conditions. The coverage of the second coat on textured surfaces can vary between 42-93 m² (450-1000 ft²) per pail because the surface becomes more sealed and smoother. For best uniformity of appearance two coats are recommended. Coverage for two coats of Weathercoat can vary from 19-42 m² (200 - 450 ft²) per pail depending upon surface being coated. Coverage will be higher on smooth, primed surfaces. A test section is recommended to determine a more accurate coverage rate.

Properties

Drying Time - Drying time of Weathercoat is dependent on the air temperature and relative humidity. Under average drying conditions [21 °C (70 °F), 55% R.H.]. Weathercoat is dry to the touch in 30 minutes and dry to handle or recoat in 2 hours. Protect work from rain for at least 24 hours.

Water Vapour Transmission

(ASTM E96) - The Weathercoat coating is permeable to water vapour.

Accelerated Weathering

(ASTM G155) - 5000 hours. No deleterious effects.

Mildew Resistance

(ASTM D3273) - Passes.

Application Procedure

Job Conditions - Air and surface temperature for application of Weathercoat must be 7 °C (45 °F) or higher and must remain so for at least 12 hours.

Surface Preparation - Surfaces shall be clean, dry, above 7 °C (45 °F) and free of efflorescence, grease, oil, form release agents and curing compounds. On previously painted surfaces, all loose, peeling and chalking paint must be removed. If it is a glossed surface, it must be removed by sanding.

Metal Surfaces - Must be primed with a corrosion-resistant primer.

EIFS Finishes - Freshly applied finishes must dry a minimum of 24 hours under average drying conditions. Existing EIFS finishes should be cleaned and flushed thoroughly with clean water.

Concrete - Shall have cured a minimum of 28 days prior to application of Weathercoat. If form release agents or curing compounds are present on the concrete surface, the surface shall be thoroughly washed with muriatic acid and flushed to remove residual acid.

Masonry - The masonry surface, with joints struck flush, may be "skim coated" with Primus®, Primus DM™ or Genesis® mixture to produce a smooth, level surface.

Stucco - Weathercoat shall be applied to the textured coat. If additives are present in the stucco, a test patch shall be made and bond strength checked prior to application.

Mixing - Stir Weathercoat to a smooth, homogeneous consistency. Avoid introducing air into the coating.

Application - Weathercoat may be applied by brush, roller or airless spray equipment. When applying by roller, a maximum 19 mm (3/4 in) nap polyester or polyester blend with nylon or lamb's wool and with bevelled ends and a phenolic core is recommended. A 460 mm (18 in) wide roller frame with 57 mm (2 1/4 in) inside diameter is also recommended. Plan the work ahead to make sure that proper staging is provided to maintain a wet

edge. Apply Weathercoat in one continuous coat, maintaining a wet edge as the application proceeds to a natural break. The roller cover must be kept fully loaded as the application proceeds. Do not stretch out the application by rolling with a dry roller. The last levelling roller strokes should always be in the same direction. Do not cut in around openings prior to overall application but, rather, do the cut-in work as the application proceeds. A 100 mm (4 in) wide roller is recommended for cutting in. Where cutting in, the Weathercoat may be thinned down with water to prevent excessive build-up.

Application Tips - Application should always be done by an experienced professional painting contractor who has a successful track record of coating masonry or EIFS. Lightly misting a surface with water ahead of an application to cool it down can help when application must be done under adverse heat conditions. The surface should not be saturated with water or overly damp when Weathercoat is applied. Some surfaces are much more porous than others. Even different elevations on the same building can vary in suction; therefore, it is difficult to get an even appearance with one coat if the surface is porous. When changing colour, always use two coats. To avoid an uneven application, do not allow Weathercoat to dry on roller covers.

Clean Up - Clean tools with water while Weathercoat is still wet.

Maintenance - All Dryvit products are designed to be virtually maintenance free. However, as with all building products, depending on location, some cleaning may be required. See Dryvit publication DSC152 on cleaning and recoating.

Storage: Weathercoat must be stored at 7 °C (45 °F) or above in tightly sealed containers out of direct sunlight.

Dryvit Systems Canada
129 Ringwood Dr.
PO Box
West Warwick, RI 02893
800-556-7752
www.dryvit.com

Information contained in this product sheet conforms to the standard detail recommendations and specifications for the installation of Dryvit Systems Canada products as of the date of publication of this document and is presented in good faith. Dryvit Systems Canada assumes no liability, expressed or implied, as to the architecture, engineering or workmanship of any project. To ensure that you are using the latest, most complete information, contact Dryvit Systems Canada

